



SPECIFICATION

IPS SOLVENT WELD WHITE SCH40 PERFORATED

IPS SOLVENT WELD PVC

Pacific Plastics IPS Schedule series of PVC pipe is produced for use in drain applications in which the maximum operating temperature is 140° F. The compound is PVC 1120 Type 1 Grade 1, with a cell class of 12454B, per ASTM D1784.

The Schedule series listed below is produced in strict compliance to ASTM D1785. It is listed with NSF and complies with NSF/ANSI Standard 14 and Standard 61.

Sch40 pipe is installed per ASTM D2855. The joints should conform to ASTM D2672, the solvent cement to ASTM D2564 and the primer to ASTM F656.

White ASTM D1785:

- Sizes 4", 6" and 8" are produced in White color, in 20 foot length and Belled End.

Perforations:

- 2 rows of holes 120° apart.
- Holes are 1 / 2" in size and are 5" on center.

The outside diameter and wall thickness of Sch40 pipe are measured in accordance to ASTM D2122 and are shown in the following tables:

DIMENSIONS

Size (inch)	OD (Outside Diameter)	T (Wall Thickness)	C (Approx Bell Depth)
4	4.500	0.237	4.00
6	6.625	0.280	6.00
8	8.625	0.322	6.00

WEIGHTS

Size (inch)	LBS/100'
4	205.00
6	362.80
8	566.00

Size
 OD Inch
 T Outside Diameter
 C Thickness
 PSI Approx. Bell Depth
 Pressure Rating

